



PO Box 375122 Cayey, PR 00737-5122
 P. 787-738-0087, 0088 Fx. 1-888-456-0656
www.technosw.com, sales@technosw.com

Technical Data Sheet

Permatex® Cold Weld Bonding Compound

AAM Revised 11/02

PRODUCT DESCRIPTION

Permatex® Cold Weld Bonding Compound is a two-part, very fast curing, high strength, general purpose adhesive and filler system. It repairs, fills and bonds to iron, steel, brass, bronze, aluminum and copper. Once this materials is cured, it can be drilled, tapped, threaded, filed and painted.

S.I.N.: 834-300

PRODUCT BENEFITS

Easy To Use:

- No heating required

Fast and Reliable:

- Holds in 10- 15 minutes
- Useable in 30 minutes
- Good moisture resistance
- Withstands extreme temperatures

Safe To Use:

- Non-flammable

TYPICAL APPLICATIONS

- Cracked transmission cases
- Chipped heads
- Rear end castings
- Cracked blocks
- Cracked intake manifolds
- Damaged keyways
- Split stampings

DIRECTIONS FOR USE

1. Before starting, make sure your work area is protected from accidental spills. Surfaces must be clean, dry and free of grease and oil.
2. Roughen smooth surfaces to be repaired with sandpaper.
3. Apply in ventilated area. Vapors may irritate eyes and nose.
4. Squeeze out equal amounts of bonding agent and curing agent.
5. Mix together thoroughly until color is uniform.
6. Apply immediately to both surfaces and press together. Remove excess glue at once.
7. Allow bond to set for 10 minutes before moving.
8. After 16 hours, typical shear strength on steel is 3000 PSI.
9. Curing time may be slower in cold weather.

For Cleanup

1. Cleanup must be completed before curing is complete. Use acetone or mineral spirits for cleanup.
2. Clean hands with Permatex® brand hand cleaners.

PROPERTIES OF UNCURED MATERIAL

	Typical Value
Chemical Type	Epoxy, amine resins

Appearance

Resin – black
 Hardener - beige

Odor

Mild

Specific Gravity (mixed)

1.79

Flash Point, TOC, °F

>400

TYPICAL CURING PERFORMANCE

Permatex® Cold Weld Bonding Compound has a gel time of 4 to 6 minutes, fixture time of 10 to 15 minutes with a full cure in 16 hours.

TYPICAL ENVIRONMENTAL RESISTANCE

Temperature Resistance

Continuous, °C (°F) Maximum 149(300)

Intermittent, °C (°F) Maximum 177(350)

Chemical / Solvent Resistance

The product retains effective properties when in contact with water, oil, fuels and solvents.

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as an adhesive for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

ORDERING INFORMATION

Part Number	Container Size
14600	2-1 oz. tubes, carded

STORAGE

Products shall be ideally stored in a cool, dry location in unopened containers at a temperature between 8° to 28°C (46° to 82°F) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container.

NOTE

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. **Permatex, Inc. specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Permatex, inc. products and disclaims any liability for consequential or incidental damages of any kind, including lost profits.** This product may be covered by one or more United States or foreign patents or patent applications.

NOT FOR PRODUCT SPECIFICATIONS.

THE TECHNICAL DATA CONTAINED HEREIN ARE INTENDED AS REFERENCE ONLY.

PLEASE CONTACT PERMATEx, INC., TECHNICAL SERVICE DEPARTMENT FOR ASSISTANCE AND RECOMMENDATIONS FOR YOUR SPECIFIC APPLICATION.
 PERMATEx, INC., HARTFORD SQUARE NORTH, 10 COLUMBUS BOULEVARD, HARTFORD, CT 06106 PHONE – (1-87PERMATEx)